

Technical Services
18 Peck Avenue
P.O. Box 148
Glens Falls, NY 12801-0148

Tel 518-793-3100
Fax 518-743-3317

To: Alisa Hoffee
From: Candy Plisko
Laboratory Technician



November 4, 2002
Report: 2297-ASTRO-White 2

Request and Purpose for Analysis

Test Pactiv ASTRO-White 2 white/Bubble/Bubble/Foil for puncture resistance on each side white bubble side, and foil side.

Method of Analysis

Puncture ASTM F 1306.

Results and Data

Test indicated that foil side puncture is stronger to penetrate through than the white bubble side.

Samples	Thickness (in)	Load at Max.Load (lb.)	Stress at Max Load (psi)
ASTRO White 2			
White Bubble side	0.2813	8.37	237.91
Foil side	0.2800	9.73	277.91